



Rustic is a 83.3% structural sound cuttings grade.

Rustic grade Alder designed to provide a knotty, natural appearance. It can be used in panels, cabinets, moldings, and much more. The knot size and quality are limited to ensure maximized value in the remanufacturing process. Graded from the best face, this product may have a high line #3 shop back, if the defect does not structurally affect the use in re-manufacturing. 6/4 and 8/4 Rustic includes any Premium that develops. These sizes are cut to minimize heart centers, pith, and maximize stability.

	6'1" (1.85m)	7'1" (2.16m)	8'1" (2.46m)	8'3" (2.52m)	10'1" (3.07m)	12'1" (3.68m)
4/4			•		•	•
5/4					•	
6/4			•		•	
8/4			•		•	
10/4			•		•	
12/4			•	•	•	

Width Specs

• 5" (127mm) minimum

Length Specs

• 84" (2.13m) minimum

Cutting Specs

• 24" (610mm) full face width cuttings

Notes

Rustic will have a surface measure yielding no less than 83.3% sound cuttings. The reverse side will grade to high line #3 Shop or better.

Cuttings will admit sound knots, bird pecks, stain, streaks, star checks, split knots, season checks, rustic appearance, pin, shot and spot worm holes. Occasional unsound knots that are not holes are not considered a defect on an otherwise exceptionally good board.

Pith is allowed up to one half the length of the board.


Wane is limited to 1" (25mm) of the width and 24" (610mm) in length on a 10' (3.04m) board, and 1" (25mm) of the width and 12" (305mm) of the length on an 96" (2.43m) board and half of the thickness.

Heavy shake are not allowed.


Stain is unlimited on the back with light stain allowed on the face. Side bend is limited to 1" (25mm).

Species Info Red Alder (Alnus rubra)

For workability, availability, and finishing, Alder is a very versatile and predictable material. It can be used alone or together with other species. Alder is a close or fine grained wood similar to cherry, birch and maple. It is used in both solid wood and veneer applications. Alder's fine homogeneous grain structure and the light uniform color of both heartwood and sapwood make it easy to form, fasten and finish.



*U.S. Department of Agriculture









www.cascadehardwood.com

800-228-3065 | sales@cascadehardwood.com

Chehalis

158 Ribelin Road. Chehalis, WA 98532 USA Phone: +1.360.748.3317

Fax: +1.360.740.5117

Port Angeles

333 Eclipse Industrial Parkway Port Angeles, WA 98363 USA Phone: +1.360.452.6041 Fax: +1.360.417.6805